

**STRONG-POINT** Get the Point. Strong-Point.

ICC

D610\_D617\_Rev. A (6/27/15)

Submittal: SDDPB0616B

## STRONG-POINT<sup>®</sup> PHILLIPS BUGLE HEAD, PHOSPHATE COATING

Size	Part#	Pt.	Case Qty.	Description
6-20 x 1	D610	2	10M	Phillips Bugle Head, Phosphate Coating
6-20 x 1-1/8	D611	2	10M	Phillips Bugle Head, Phosphate Coating
6-20 x 1-1/4	D614	2	8M	Phillips Bugle Head, Phosphate Coating
6-20 x 1-5/8	D615	2	5M	Phillips Bugle Head, Phosphate Coating
6-20 x 1-7/8	D617	2	4M	Phillips Bugle Head, Phosphate Coating
Application	Attachae av	neum ine	ulation and wood	to motal

Application: Attaches gypsum, insulation and wood to metal.

Drill Capacity (in.): .035 - .090

- Specifications: Meets ASTM<sup>1</sup> A 510 for carbon steel manufacturing
  - Meets ASTM C 954 for attaching gypsum board to steel studs
  - Manufactured to SAE<sup>2</sup> J78 for dimensional specifications
  - Meets F.I.P.<sup>3</sup>-1000.7 for torsional strength and drill speed
  - ICC-ES Evaluation Report: ESR-3528

Installation: A standard screw gun with torque limiting nose piece set at a maximum of 2500 RPM drive speed recommended. Use a #2 reduced Phillips drive bit. Do not over torque as it can cause the head to snap or stripping of the recess. The bugle head fastener is properly seated when the head sits flush or slightly countersunk with the sheathing surface. Installed fasteners must penetrate a minimum of three full threads beyond the metal structure.

				Pullout Value	es (Avg. Lbs.)	)					
Fastener		Steel Gauge									
Size	Pt.	22	20	18	16	14	12	1/8	3/16		
6-20	2	126	218	366	496	825	1004				
Shear Values (Avg. Lbs.)											
Fastener			Steel Gauge (Lapped)								
Size	Pt.	22	20	18	16	14	12	1/8	3/16		
6-20	2	444	721	875	912						

The values listed are averages achieved under laboratory conditions and imply no warranty. Appropriate safety factors should be applied to these values for design purposes.

<sup>1</sup>(American Society of Testing Materials)

<sup>2</sup>(Society of Automotive Engineers)

<sup>3</sup>(Fastener Inspection Products)

Los Angeles	New York	Chicago	Dallas	Atlanta	Portland	Houston	Cleveland	Miami
800.762.2004	888.322.2262	800.533.9669	800.558.7222	800.822.9690	800.434.5606	800.558.7222	800.533.9669	800.822.9690